

## Polyram Bondyram® 7103 Maleic Anhydride Modified Ethylene-Alpha Olefin Copolymer

Category : Polymer , Thermoplastic , Polyethylene (PE) , Anhydride-Modified Polyethylene

### Material Notes:

High flow impact modified for Nylon compounds un-reinforced and glass fiber reinforced. Good retention of impact at low temperatures. Information provided by Polyram.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polyram-Bondyram-7103-Maleic-Anhydride-Modified-Ethylene-Alpha-Olefin-Copolymer.php](http://www.lookpolymers.com/polymer_Polyram-Bondyram-7103-Maleic-Anhydride-Modified-Ethylene-Alpha-Olefin-Copolymer.php)

Physical Properties	Metric	English	Comments
Density	0.880 g/cc	0.0318 lb/in <sup>3</sup>	ISO 1183
Melt Flow	1.5 g/10 min @Load 2.16 kg, Temperature 190 °C	1.5 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China