

Polyram PlusTek PA100 Nylon 6.6, General Purpose

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Unreinforced

Material Notes:

General purpose polyamide 6.6 for injection molding applicationsInformation provided by Polyram Ram On Ind.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-PlusTek-PA100-Nylon-66-General-Purpose.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	DIN 53479
Water Absorption	8.5 %	8.5 %	DIN 53495
Moisture Absorption at Equilibrium	2.8 %	2.8 %	50%RH; DIN 53714
Linear Mold Shrinkage	0.014 - 0.018 cm/cm	0.014 - 0.018 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM-D785
Tensile Strength, Yield	85.0 MPa	12300 psi	ASTM-D638
Elongation at Break	4.0 %	4.0 %	ASTM-D638
Flexural Strength	120 MPa	17400 psi	ASTM D790
Flexural Modulus	2.70 GPa	392 ksi	ASTM-D790
Izod Impact, Notched	0.550 J/cm @Temperature 23.0 °C	1.03 ft-lb/in @Temperature 73.4 °F	ASTM-D256

Thermal Properties	Metric	English	Comments
Melting Point	256 °C	493 °F	
Maximum Service Temperature, Air	80.0 °C	176 °F	Continuous Use
	200 °C	392 °F	Short peaks operation
Deflection Temperature at 0.46 MPa (66 psi)	210 °C	410 °F	DIN 53461
Deflection Temperature at 1.8 MPa (264 psi)	100 °C	212 °F	DIN 53461
Flammability, UL94	V-2 @Thickness 3.00 mm	V-2 @Thickness 0.118 in	
Glow Wire Test	750 °C	1380 °F	

Thermal Properties	Metric	English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	DIN 53482
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	DIN 53482
Dielectric Constant	3.6	3.6	VDE 0303/4
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	120 kV/mm	3050 kV/in	VDE 0303/4

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China