

## Polyram PlusTek PA360G6 Nylon 6.6, 30% Glass Fiber

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

### Material Notes:

30% glass fiber reinforced with molybdenum disulfide polyamide 6.6 for injection molding applications Information provided by Polyram Ram On Ind.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polyram-PlusTek-PA360G6-Nylon-66-30-Glass-Fiber.php](http://www.lookpolymers.com/polymer_Polyram-PlusTek-PA360G6-Nylon-66-30-Glass-Fiber.php)

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in <sup>3</sup>	DIN 53479
Water Absorption	5.5 %	5.5 %	DIN 53495
Moisture Absorption at Equilibrium	1.8 %	1.8 %	50%RH; DIN 53714
Linear Mold Shrinkage	0.0090 - 0.013 cm/cm	0.0090 - 0.013 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	122	122	ASTM-D785
Tensile Strength, Yield	170 MPa	24700 psi	ASTM-D638
Elongation at Break	3.0 %	3.0 %	ASTM-D638
Flexural Strength	240 MPa	34800 psi	ASTM D790
Flexural Modulus	8.50 GPa	1230 ksi	ASTM-D790
Izod Impact, Notched	0.900 J/cm @Temperature 23.0 °C	1.69 ft-lb/in @Temperature 73.4 °F	ASTM-D256

Thermal Properties	Metric	English	Comments
Melting Point	256 °C	493 °F	
Maximum Service Temperature, Air	120 °C	248 °F	Continuous Use
	240 °C	464 °F	Short peaks operation
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	DIN 53461
Deflection Temperature at 1.8 MPa (264 psi)	250 °C	482 °F	DIN 53461
Flammability, UL94	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	DIN 53482
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	DIN 53482
Dielectric Constant	3.7	3.7	VDE 0303/4
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	80.0 kV/mm	2030 kV/in	VDE 0303/4

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China