

Polyram PlusTek PA840G7 Nylon 6.6 for Injection Molding, 35% Glass Fibers Reinforced, Impact Modified

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Glass Reinforced, Impact Grade

Material Notes:

35% Glass fiber reinforced, impact modified Nylon 6.6 for injection molding applications. Information provided by Polyram.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-PlusTek-PA840G7-Nylon-66-for-Injection-Molding-35-Glass-Fibers-Reinforced-Impact-Modified.php

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	1.7 %	1.7 %	50% RH; ISO 62
Water Absorption at Saturation	5.6 %	5.6 %	ISO 62
Linear Mold Shrinkage	0.0030 - 0.0070 cm/cm	0.0030 - 0.0070 in/in	ISO 2577

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	122	122	
Tensile Strength, Yield	155 MPa	22500 psi	ISO 527
Elongation at Break	3.0 %	3.0 %	ISO 527
Flexural Strength	220 MPa	31900 psi	ISO 178
Flexural Modulus	7.50 GPa	1090 ksi	ISO 178
Izod Impact, Notched (ISO)	18.0 kJ/m ²	8.57 ft-lb/in ²	ISO 180

Thermal Properties	Metric	English	Comments
Melting Point	256 °C	493 °F	ISO 11357
Maximum Service Temperature, Air	110 °C	230 °F	Continuous use
	250 °C	482 °F	Short peaks operation
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	240 °C	464 °F	ISO 75
Flammability, UL94	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	IEC 60093
Dielectric Constant	3.5	3.5	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	90.0 kV/mm	2290 kV/in	IEC 60250

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China