

Polyram PlusTek PD300G6 Nylon 12, 30% Glass Fiber

Category : Polymer , Thermoplastic , Nylon , Nylon 12 , Nylon 12, 30% Glass Fiber Filled

Material Notes:

30% glass-fiber reinforced polyamide 12 for injection molding applications Information provided by Polyram Ram On Ind.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-PlusTek-PD300G6-Nylon-12-30-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	DIN 53479
Water Absorption	1.2 %	1.2 %	DIN 53495

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	115 MPa	16700 psi	ASTM-D638
Elongation at Break	3.5 %	3.5 %	ASTM-D638
Tensile Modulus	8.00 GPa	1160 ksi	ASTM-D790
Flexural Strength	170 MPa	24700 psi	ASTM D790
Flexural Modulus	5.80 GPa	841 ksi	ASTM-D790
Izod Impact, Notched	1.10 J/cm @Temperature 23.0 °C	2.06 ft-lb/in @Temperature 73.4 °F	ASTM-D256

Thermal Properties	Metric	English	Comments
Melting Point	165 - 175 °C	329 - 347 °F	
Flammability, UL94	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China