

## Polyram PlusTek RB306G6 Nylon 6, 30% Glass Fiber

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled

### Material Notes:

30% glass-fiber reinforced. Heat stabilized polyamide 6 for injection molding applications Information provided by Polyram Ram On Ind.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polyram-PlusTek-RB306G6-Nylon-6-30-Glass-Fiber.php](http://www.lookpolymers.com/polymer_Polyram-PlusTek-RB306G6-Nylon-6-30-Glass-Fiber.php)

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in <sup>3</sup>	DIN 53479
Water Absorption	6.6 %	6.6 %	DIN 53495
Moisture Absorption at Equilibrium	2.1 %	2.1 %	50%RH; DIN 53714
Linear Mold Shrinkage	0.0035 cm/cm	0.0035 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	122	122	ASTM-D785
Tensile Strength, Yield	140 MPa	20300 psi	ASTM-D638
Elongation at Break	2.5 %	2.5 %	ASTM-D638
Flexural Strength	200 MPa	29000 psi	ASTM D790
Flexural Modulus	7.00 GPa	1020 ksi	ASTM-D790
Izod Impact, Notched	0.800 J/cm @Temperature 23.0 °C	1.50 ft-lb/in @Temperature 73.4 °F	ASTM-D256

Thermal Properties	Metric	English	Comments
Melting Point	208 °C	406 °F	
Maximum Service Temperature, Air	110 °C	230 °F	Continuous Use
	200 °C	392 °F	Short peaks operation
Deflection Temperature at 0.46 MPa (66 psi)	217 °C	423 °F	DIN 53461
Deflection Temperature at 1.8 MPa (264 psi)	205 °C	401 °F	DIN 53461
Flammability, UL94	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**