

Polyram Polytron P50B03 Copolymer Polypropylene, Chemically Coupled 50% Long Glass Fiber

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 50% Glass Fiber Filler

Material Notes:

A CHEMICALLY COUPLED 50% LONG GLASS FIBER REINFORCED BLACK POLYPROPYLENE HEAT STABILIZED FOR INJECTION MOLDING APPLICATION. These products have significantly improved impact performance characteristics compared to other grades of Polypropylene long fiber thermoplastics. The room temperature Charpy impact properties are 25 to 30% higher at room temperature and at low temperature (-40 C). Information provided by Polyram Ram On Ind.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-Polytron-P50B03-Copolymer-Polypropylene-Chemically-Coupled-50-Long-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	ASTM-D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	120 MPa	17400 psi	ASTM-D638
Elongation at Break	2.1 %	2.1 %	ASTM-D638
Tensile Modulus	9.50 GPa	1380 ksi	ASTM-D790
Flexural Strength	200 MPa	29000 psi	ASTM-D790
Flexural Modulus	9.20 GPa	1330 ksi	ASTM-D790
Izod Impact, Notched	3.50 J/cm @Temperature 23.0 °C	6.56 ft-lb/in @Temperature 73.4 °F	ASTM-D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	153 °C	307 °F	ASTM-D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China