

Polyram Polytron P50N01 Homopolymer Polypropylene, Chemically Coupled 50% Long Glass Fiber

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 50% Glass Fiber Filler

Material Notes:

A CHEMICALLY COUPLED 50% LONG GLASS FIBER REINFORCED NATURAL POLYPROPYLENE HEAT STABILIZED FOR INJECTION MOLDING APPLICATION. Information provided by Polyram Ram On Ind.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-Polytron-P50N01-Homopolymer-Polypropylene-Chemically-Coupled-50-Long-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.31 g/cc	0.0473 lb/in ³	ASTM-D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	135 MPa	19600 psi	ASTM-D638
Elongation at Break	2.0 %	2.0 %	ASTM-D638
Tensile Modulus	13.9 GPa	2020 ksi	ASTM-D790
Flexural Strength	210 MPa	30500 psi	ASTM-D790
Flexural Modulus	11.0 GPa	1600 ksi	ASTM-D790
Izod Impact, Notched	2.50 J/cm @Temperature 23.0 °C	4.68 ft-lb/in @Temperature 73.4 °F	ASTM-D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	159 °C	318 °F	ASTM-D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China