

## Polyram Polytron P60B11 Homopolymer Polypropylene, Chemically Coupled 60% LGF

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 60% Glass Fiber Filler

**Material Notes:**

A chemically coupled 60% LGF reinforced black PP, heat stabilized for injection molding applications. Information provided by Polyram Ram On Ind.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polyram-Polytron-P60B11-Homopolymer-Polypropylene-Chemically-Coupled-60-LGF.php](http://www.lookpolymers.com/polymer_Polyram-Polytron-P60B11-Homopolymer-Polypropylene-Chemically-Coupled-60-LGF.php)

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in <sup>3</sup>	ASTM-D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	150 MPa	21800 psi	ASTM-D638
Elongation at Break	2.0 %	2.0 %	ASTM-D638
Tensile Modulus	15.1 GPa	2190 ksi	ASTM-D790
Flexural Strength	230 MPa	33400 psi	ASTM-D790
Flexural Modulus	13.9 GPa	2020 ksi	ASTM-D790
Izod Impact, Notched	2.90 J/cm @Temperature 23.0 °C	5.43 ft-lb/in @Temperature 73.4 °F	ASTM-D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	159 °C	318 °F	ASTM-D648

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China