

## Polyram RamOfin PPH300G4 Polypropylene, 20% Glass Fiber

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Glass Fiber Filler

### Material Notes:

20% glass fiber reinforced polypropylene for injection molding applications Information provided by Polyram Ram On Ind.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polyram-RamOfin-PPH300G4-Polypropylene-20-Glass-Fiber.php](http://www.lookpolymers.com/polymer_Polyram-RamOfin-PPH300G4-Polypropylene-20-Glass-Fiber.php)

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in <sup>3</sup>	DIN 53479
Linear Mold Shrinkage	0.032 cm/cm	0.032 in/in	
Melt Flow	5.0 g/10 min @Load 2.16 kg, Temperature 230 °C	5.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	70.0 MPa	10200 psi	ASTM-D638
Elongation at Break	3.0 %	3.0 %	ASTM-D638
Tensile Modulus	4.80 GPa	696 ksi	ASTM-D790
Flexural Strength	100 MPa	14500 psi	ASTM D790
Flexural Modulus	3.20 GPa	464 ksi	ASTM-D790
Izod Impact, Notched	0.950 J/cm @Temperature 23.0 °C	1.78 ft-lb/in @Temperature 73.4 °F	ASTM-D256

Thermal Properties	Metric	English	Comments
Melting Point	165 °C	329 °F	
Maximum Service Temperature, Air	110 °C	230 °F	Continuous Use
	140 °C	284 °F	Short peaks operation
Deflection Temperature at 0.46 MPa (66 psi)	153 °C	307 °F	DIN 53461
Deflection Temperature at 1.8 MPa (264 psi)	145 °C	293 °F	DIN 53461
Flammability, UL94	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**