

Polyram RamTal PMH2010 Polyacetal Homopolymer for Injection Molding

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Homopolymer, Unreinforced

Material Notes:

General purpose polyacetal homopolymer for injection molding applications, MFI 10. Information provided by Polyram.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-RamTal-PMH2010-Polyacetal-Homopolymer-for-Injection-Molding.php

Physical Properties	Metric	English	Comments
Density	1.42 g/cc	0.0513 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.018 - 0.022 cm/cm	0.018 - 0.022 in/in	ISO 2577
Melt Flow	10 g/10 min @Load 2.16 kg, Temperature 190 °C	10 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	90.0 MPa	13100 psi	ISO 527
Elongation at Break	60 %	60 %	ISO 527
Flexural Strength	105 MPa	15200 psi	ISO 178
Flexural Modulus	3.00 GPa	435 ksi	ISO 178
Izod Impact, Notched (ISO)	10.0 kJ/m ²	4.76 ft-lb/in ²	ISO 180

Thermal Properties	Metric	English	Comments
Melting Point	165 °C	329 °F	ISO 11357
Deflection Temperature at 0.46 MPa (66 psi)	165 °C	329 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	100 °C	212 °F	ISO 75
Flammability, UL94	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China