

## Polyram RamTal PMH2017 Polyacetal Homopolymer for Injection Molding

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Homopolymer, Unreinforced

**Material Notes:**

General purpose polyacetal homopolymer for injection molding applications, MFI 1.7. Information provided by Polyram.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polyram-RamTal-PMH2017-Polyacetal-Homopolymer-for-Injection-Molding.php](http://www.lookpolymers.com/polymer_Polyram-RamTal-PMH2017-Polyacetal-Homopolymer-for-Injection-Molding.php)

Physical Properties	Metric	English	Comments
Density	1.42 g/cc	0.0513 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage	0.018 - 0.022 cm/cm	0.018 - 0.022 in/in	ISO 2577
Melt Flow	1.7 g/10 min @Load 2.16 kg, Temperature 190 °C	1.7 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	72.0 MPa	10400 psi	ISO 527
Elongation at Break	40 %	40 %	ISO 527
Tensile Modulus	3.00 GPa	435 ksi	ISO 527
Charpy Impact, Notched	0.900 J/cm <sup>2</sup>	4.28 ft-lb/in <sup>2</sup>	ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	165 °C	329 °F	ISO 11357
Deflection Temperature at 0.46 MPa (66 psi)	165 °C	329 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	100 °C	212 °F	ISO 75
Flammability, UL94	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China