

Potters Industries Spheriglass® 3000E Solid Glass Spheres

Category : Ceramic , Glass , Oxide , Silicon Oxide , Other Engineering Material , Additive/Filler for Polymer

Material Notes:

Description: Spheriglass® fine solid glass spheres are used as an additive for thermoplastic and thermosetting resin systems. Glass spheres give products many benefits such as: Low Uniform Shrinkage, Low Warpage, High Flexural Modulus, High Abrasion Resistance, High Compressive Strength, Increased Surface Hardness, Better Stress Distribution. These and other characteristics enable the spheres to be used in a wide range of applications in the automotive, chemical, electronic, industrial, engineering, and photographic industries. Information provided by Potters Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Potters-Industries-Spheriglass-3000E-Solid-Glass-Spheres.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.54 g/cc	2.54 g/cc	
Bulk Density	1.31 g/cc	0.0475 lb/in ³	Untapped; ASTM D 3101-78
	1.60 g/cc	0.0579 lb/in ³	Tapped; ASTM D 3101-78
Oil Absorption	18 %	18 %	ASTM D1483
Particle Size	30 - 50 µm	30 - 50 µm	mean value
Particle Mesh Size	325 Mesh	325 Mesh	

Mechanical Properties	Metric	English	Comments
Hardness, Mohs	6.5	6.5	
Modulus of Elasticity	72.4 GPa	10500 ksi	
Coefficient of Friction	1.0	1.0	

Thermal Properties	Metric	English	Comments
CTE, linear	2.80 µm/m-°C	1.56 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Softening Point	846 °C	1550 °F	

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	14.5 %	14.5 %	
B ₂ O ₃	8.6 %	8.6 %	
CaO	22.5 %	22.5 %	

Component Elements Properties	Metric	English	Comments
Free Iron	<= 0.10 %	<= 0.10 %	
K2O	0.20 %	0.20 %	
MgO	1.2 %	1.2 %	
Na2O	0.30 %	0.30 %	
SiO2	52.5 %	52.5 %	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 - 1.00e+16 ohm-cm	1.00e+13 - 1.00e+16 ohm-cm	
Dielectric Constant	5.8 @Frequency 1e+6 Hz	5.8 @Frequency 1e+6 Hz	
Dissipation Factor	0.0010 @Frequency 1e+6 Hz	0.0010 @Frequency 1e+6 Hz	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China