

Precision Polymer Engineering C40M Chloroprene Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Chlorosulfonated Polyethylene Rubber

Material Notes:

Chloroprene elastomer, 36-45 °IRHD. Formulated to BS 2752 grade C40. Applications: A versatile rubber with good compression set properties, giving moderate resistance to petroleum based oils, ozone and weather.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-C40M-Chloroprene-Rubber.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	38	38	°IRHD; ASTM D1415
	44	44	°IRHD, +6 change after 168 hours @ 70°C; ASTM D1415
Tensile Strength, Yield	12.68 MPa	1839 psi	-0.5% change after 168 hours @ 70°C; ASTM D412
	12.74 MPa	1848 psi	ASTM D412
Elongation at Break	476.19 %	476.19 %	-1% change after 168 hours @ 70°C; ASTM D412
	481 %	481 %	ASTM D412
Compression Set	33 %	33 %	24 hours @ 70°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	125 °C	257 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	
	-40.0 °C	-40.0 °F	Non-brittle after 3 minutes
Flash Point	>= 260 °C	>= 500 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China