

Precision Polymer Engineering E50E Ethylene Propylene Rubber

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE)

Material Notes:

Ethylene Propylene Terpolymer, 46-55 °IRHD. Terpolymer of ethylene, propylene and diene monomers. To meet Aerospace Specification DTD5597A Grade 50.Applications: For sealing applications where good fluid resistance and low compression set are of prime importance. For continuous and/or intermittent use in contact with phosphate ester or silicone hydraulic fluids within the temperature ranges as quoted. Suitable for applications in contact with air, this material has excellent resistance to ozone. Unsuitable for use in contact with fuels, mineral oil based and diester oils and silicate fluids or greases derived from these.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-E50E-Ethylene-Propylene-Rubber.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50	50	°IRHD; ASTM D1415
	65	65	°IRHD, +15 change after 168 hours @ 125°C; ASTM D1415
Tensile Strength, Yield	8.00 MPa	1160 psi	-20% change after 168 hours @ 125°C; ASTM D412
	10.0 MPa	1450 psi	ASTM D412
Elongation at Break	320 %	320 %	-20% change after 168 hours @ 125°C; ASTM D412
	400 %	400 %	ASTM D412
Compression Set	25 %	25 %	24 hours @ 100°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	160 °C	320 °F	
Minimum Service Temperature, Air	-60.0 °C	-76.0 °F	
	-45.0 °C	-49.0 °F	Non-brittle after 3 minutes
Flash Point	>= 200 °C	>= 392 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China