

Precision Polymer Engineering E70E Ethylene Propylene Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Ethylene Propylene Terpolymer, 66-75 °IRHD. Terpolymer of ethylene, propylene and diene monomers. To meet Aerospace Specification DTD5597A Grade 70. Applications: For sealing applications where good fluid resistance and low compression set are of prime importance. For continuous and/or intermittent use in contact with phosphate ester or silicone hydraulic fluids within the temperature ranges as quoted. Suitable for applications in contact with air, this material has excellent resistance to ozone. Unsuitable for use in contact with fuels, mineral oil based and diester oils and silicate fluids or greases derived from these.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-E70E-Ethylene-Propylene-Rubber.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	°IRHD; ASTM D1415
	70 - 85	70 - 85	°IRHD, 0 to +10 change after 168 hours @ 125°C; ASTM D1415
Tensile Strength, Yield	9.35 MPa	1360 psi	-15% change after 168 hours @ 125°C; ASTM D412
	11.0 MPa	1600 psi	ASTM D412
Elongation at Break	200 %	200 %	-20% change after 168 hours @ 125°C; ASTM D412
	250 %	250 %	ASTM D412
Compression Set	20 %	20 %	24 hours @ 100°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	160 °C	320 °F	
Minimum Service Temperature, Air	-60.0 °C	-76.0 °F	
	-45.0 °C	-49.0 °F	Non-brittle after 3 minutes
Flash Point	>= 200 °C	>= 392 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China