

Precision Polymer Engineering E70V Ethylene Propylene Rubber

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE)

Material Notes:

Peroxide cured, blue-violet Ethylene Propylene Terpolymer, 65-75 °IRHD. Terpolymer of ethylene, propylene and diene monomers. Specially formulated for sealing applications involving high voltage electrical equipment. Applications: For sealing sulphur hexafluoride (SF6) gas in electrical distribution equipment, i.e. medium & high voltage switchgear, also scientific equipment such as X-ray generators, electrostatic particle accelerators and electron microscopes. The specially selected fillers used in this compound provide excellent electrical non-conductive properties to the rubber.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-E70V-Ethylene-Propylene-Rubber.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	°IRHD; ASTM D1415
Tensile Strength, Yield	8.00 MPa	1160 psi	ASTM D412
Elongation at Break	250 %	250 %	ASTM D412
Compression Set	15 %	15 %	70 hours @ 100°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 °C	302 °F	
Minimum Service Temperature, Air	-50.0 °C	-58.0 °F	
	-45.0 °C	-49.0 °F	Non-brittle after 3 minutes
Flash Point	>= 200 °C	>= 392 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China