

## Precision Polymer Engineering E70X Ethylene Propylene Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Peroxide cured, Ethylene Propylene Rubber, 65-75 °IRHD. Copolymer of ethylene and propylene. Applications: Excellent water and steam resistance with good compression set properties. Superior heat and chemical resistance compared to sulphur cured EPDM. Not oil resistant.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Precision-Polymer-Engineering-E70X-Ethylene-Propylene-Rubber.php](http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-E70X-Ethylene-Propylene-Rubber.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	°IRHD; ASTM D1415
	80	80	°IRHD, +10 change after 70 hours @ 125°C; ASTM D1415
Tensile Strength, Yield	8.00 MPa	1160 psi	-20% change after 70 hours @ 125°C; ASTM D412
	10.0 MPa	1450 psi	ASTM D412
Elongation at Break	120 %	120 %	-40% change after 70 hours @ 125°C; ASTM D412
	200 %	200 %	ASTM D412
Compression Set	10 %	10 %	22 hours @ 100°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 °C	302 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	
	-40.0 °C	-40.0 °F	Non-brittle after 3 minutes
Flash Point	>= 200 °C	>= 392 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China