

## Precision Polymer Engineering F60R Fluorosilicone Rubber

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE) , Silicone

### Material Notes:

Red Fluorosilicone, 56-65 °IRHD. Fluorosilicone rubber having methyl, vinyl and fluorine substituent groups on the polymer chain. To meet Aerospace Specification DTD5583A Grade 60. Applications: Sealing petroleum-based fuels, hydraulic fluids and lubricants, and with silicone and certain ester-based fluids (but excluding certain phosphate esters).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Precision-Polymer-Engineering-F60R-Fluorosilicone-Rubber.php](http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-F60R-Fluorosilicone-Rubber.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	63	63	°IRHD, -1 change after 336 hours @ 200°C; ASTM D1415
	64	64	°IRHD; ASTM D1415
Tensile Strength, Yield	5.59 MPa	811 psi	-35% change after 336 hours @ 200°C; ASTM D412
	8.60 MPa	1250 psi	ASTM D412
Elongation at Break	263.72 %	263.72 %	-24% change after 336 hours @ 200°C; ASTM D412
	347 %	347 %	ASTM D412
Compression Set	8.0 %	8.0 %	24 hours @ 150°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	250 °C	482 °F	
Minimum Service Temperature, Air	-65.0 °C	-85.0 °F	
	-50.0 °C	-58.0 °F	Temperature at which modulus shall not exceed 70 Mpa
Flash Point	>= 300 °C	>= 572 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China