

Precision Polymer Engineering H50B Epichlorohydrin

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Peroxide Cured, Epichlorohydrin Rubber, 45-55 °IRHD. Terpolymer of epichlorohydrin, ethylene oxide and an unsaturated monomer. ASTM and ISO designation = GECO. Applications: Excellent resistance to petroleum based oils and fuels. Becoming widely used in military and automotive applications where its low and high temperature operating range is superior to that of nitrile. Good resistance to water, acids, ozone and weathering.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-H50B-Epichlorohydrin.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50	50	°IRHD; ASTM D1415
	50 - 65	50 - 65	°IRHD, 0 to +15 change after 72 hours @ 150°C; ASTM D1415
Tensile Strength, Yield	6.00 MPa	870 psi	-25% change after 72 hours @ 150°C; ASTM D412
	8.00 MPa	1160 psi	ASTM D412
Elongation at Break	125 %	125 %	-50% change after 72 hours @ 150°C; ASTM D412
	250 %	250 %	ASTM D412
Compression Set	25 %	25 %	22 hours @ 100°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 °C	302 °F	
Minimum Service Temperature, Air	-50.0 °C	-58.0 °F	
	-40.0 °C	-40.0 °F	Non-brittle after 3 minutes
Flash Point	>= 250 °C	>= 482 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China