

Precision Polymer Engineering Perlast® G60H Perfluoroelastomer

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Special, pure white compound with excellent high temperature properties and wide chemical resistance. Extremely low outgassing properties. Applications: For use in applications which require exposure to temperatures in excess of 260°C (500°F) and shorter term to 310°C (590°F). Recommended for use in the semiconductor industry. Do not use any Perlast ® grade with molten alkali metals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-Perlast-G60H-Perfluoroelastomer.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	58	58	°IRHD, -2 change after 72 hours @ 260°C; ASTM D1415
	60	60	°IRHD; ASTM D1415
Tensile Strength, Yield	13.0 MPa	1890 psi	ASTM D412
	14.3 MPa	2070 psi	10% change after 72 hours @ 260°C; ASTM D412
Elongation at Break	237.5 %	237.5 %	-5% change after 72 hours @ 260°C; ASTM D412
	250 %	250 %	ASTM D412
100% Modulus	0.00720 GPa	1.04 ksi	-10% change after 72 hours @ 260°C; ASTM D412
	0.00800 GPa	1.16 ksi	ASTM D412
Compression Set	19 %	19 %	24 hours @ 200°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	310 °C	590 °F	
Minimum Service Temperature, Air	-15.0 °C	5.00 °F	
Flash Point	>= 400 °C	>= 752 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China