

Precision Polymer Engineering S60K Silicone Rubber

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE), Silicone

Material Notes:

Silicone Rubber, 56-65 °IRHD. Silicone rubber having both methyl and vinyl substituent groups on the polymer chain. Formulated using only those ingredients determined by the United States Federal Food and Drug Administration (FDA) to be in accordance with Code of Federal Regulations, Title 21 (CFR21), Section 177.2600. Formulated to BS2494 Type 'W' and Water Research Council (WRC) tested in accordance with BS6920 'Items which have passed full tests of effects on water quality' (for use in potable water applications). ASTM & ISO designation = VMQ. WRC Approval No. 9910521.Applications: Cold and hot water, plus low-pressure steam, up to +110°C.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-S60K-Silicone-Rubber.php

| Mechanical Properties | Metric | English | Comments |
|-------------------------|-----------------|-----------------|--|
| Hardness, Shore A | 60 | 60 | °IRHD; ASTM D1415 |
| | 55 - 65 | 55 - 65 | °IRHD, ±5 change after 168 hours @ 70°C; ASTM D1415 |
| Tensile Strength, Yield | 9.00 MPa | 1310 psi | ASTM D412 |
| | 7.20 - 10.8 MPa | 1040 - 1570 psi | ±20% change after 168 hours @ 70°C; ASTM D412 |
| Elongation at Break | 300 % | 300 % | ASTM D412 |
| | 210 - 390 % | 210 - 390 % | ±30% change after 168 hours @ 70°C; ASTM D412 |
| Compression Set | 20 % | 20 % | 24 hours @ 70°C; ASTM D395 |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|-----------|-----------|-----------------------------|
| Maximum Service Temperature, Air | 250 °C | 482 °F | |
| Minimum Service Temperature, Air | -60.0 °C | -76.0 °F | |
| | -60.0 °C | -76.0 °F | Non-brittle after 3 minutes |
| Flash Point | >= 300 °C | >= 572 °F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China