

Precision Polymer Engineering S65G Silicone Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone

Material Notes:

Low Compression Set, Green Silicone Rubber, 65-75 °IRHD. Silicone rubber having both methyl and vinyl substituent groups on the polymer chain. ASTM & ISO designation = VMQ. Applications: Low compression set grade, offering excellent heat resistance and low temperature flexibility. Used primarily for dry heat static seals, low physical strength and poor abrasion resistance prevents dynamic sealing.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-S65G-Silicone-Rubber.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	°IRHD; ASTM D1415
	60 - 80	60 - 80	°IRHD, ±10 change after 70 hours @ 200°C; ASTM D1415
Tensile Strength, Yield	4.275 MPa	620.0 psi	-25% change after 70 hours @ 200°C; ASTM D412
	5.70 MPa	827 psi	ASTM D412
Elongation at Break	82.5 %	82.5 %	-45% change after 70 hours @ 200°C; ASTM D412
	150 %	150 %	ASTM D412
Compression Set	15 %	15 %	24 hours @ 175°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	250 °C	482 °F	
Minimum Service Temperature, Air	-60.0 °C	-76.0 °F	
	-60.0 °C	-76.0 °F	Non-brittle after 3 minutes
Flash Point	>= 300 °C	>= 572 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China