

Precision Polymer Engineering S70N Silicone Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone

Material Notes:

Silicone Rubber, 66-75 °IRHD. Silicone rubber having both methyl and vinyl substituent groups on the polymer chain. To meet UK Ministry of Defence Aircraft Materials Specification DTD5582A Grade 70. Applications: Particularly suitable in fluid sealing applications where low compression set is of prime importance in O-rings and gaskets. Can be used in contact with heavy mineral and certain diester-based oils within the quoted temperature range. Unsuitable for use in contact with petroleum based fuels, light mineral oils or greases derived from them. Excellent ozone resistance.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-S70N-Silicone-Rubber.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	°IRHD; ASTM D1415
	67 - 75	67 - 75	°IRHD, -3/+5 change after 70 hours @ 200°C; ASTM D1415
Tensile Strength, Yield	4.40 MPa	638 psi	-20% change after 70 hours @ 200°C; ASTM D412
	5.50 MPa	798 psi	ASTM D412
Elongation at Break	75 %	75 %	-25% change after 70 hours @ 200°C; ASTM D412
	100 %	100 %	ASTM D412
Compression Set	20 %	20 %	24 hours @ 150°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	250 °C	482 °F	
Minimum Service Temperature, Air	-65.0 °C	-85.0 °F	Non-brittle after 3 minutes
	-60.0 °C	-76.0 °F	
Flash Point	>= 300 °C	>= 572 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China