

Precision Polymer Engineering V60D Fluoroelastomer Compound

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Fluoroelastomer Rubber, 55-65 °IRHD. Copolymer of vinylidene fluoride and hexafluoropropylene. To meet Aerospace Specifications DTD5612A and DTD5543B Grade 60. Applications: Mouldings which are required to operate within the approximate temperature range of -20° to +225°C, in contact with air, petroleum, silicone and diester-based liquids. The material is not suitable for use in contact with certain phosphate-ester-based liquids.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-V60D-Fluoroelastomer-Compound.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	°IRHD; ASTM D1415
	60	60	°IRHD, 0 change after 72 hours @ 250°C; ASTM D1415
Tensile Strength, Yield	15.865 MPa	2301.0 psi	-5% change after 72 hours @ 250°C; ASTM D412
	16.7 MPa	2420 psi	ASTM D412
Elongation at Break	260 %	260 %	ASTM D412
	265.2 %	265.2 %	2% change after 72 hours @ 250°C; ASTM D412
Compression Set	5.0 %	5.0 %	24 hours @ 200°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	225 °C	437 °F	
Minimum Service Temperature, Air	-20.0 °C	-4.00 °F	
Flash Point	>= 315 °C	>= 599 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China