

Precision Polymer Engineering V60E Fluoroelastomer Compound

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Litharge Incorporated, Green Fluoroelastomer Rubber, 55-65 °IRHD. Copolymer of vinylidene fluoride and hexafluoropropylene. To meet ASTM D2000 line call-out M2HK610, A1-10, B38, EF31, EO78, F15, Z1, where Z1 = colour green. ASTM designation = FKM. ISO designation = FPM. Applications: Litharge incorporated for increased resistance to acids and aqueous media.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-V60E-Fluoroelastomer-Compound.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	°IRHD; ASTM D1415
	70	70	°IRHD, +10 change after 72 hours @ 250°C; ASTM D1415
Tensile Strength, Yield	7.50 MPa	1090 psi	-25% change after 72 hours @ 250°C; ASTM D412
	10.0 MPa	1450 psi	ASTM D412
Elongation at Break	150 %	150 %	-25% change after 72 hours @ 250°C; ASTM D412
	200 %	200 %	ASTM D412
Compression Set	50 %	50 %	24 hours @ 200°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	
Minimum Service Temperature, Air	-20.0 °C	-4.00 °F	
Flash Point	>= 315 °C	>= 599 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China