

Precision Polymer Engineering V65B Fluoroelastomer Compound

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Fluoroelastomer Rubber, 61-70 °IRHD. Copolymer of vinylidene fluoride and hexafluoropropylene. Applications: Excellent resistance to oils, fuels and hydraulic fluids at high temperature.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-V65B-Fluoroelastomer-Compound.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	64	64	°IRHD; ASTM D1415
	69	69	°IRHD, +5 change after 72 hours @ 250°C; ASTM D1415
Tensile Strength, Yield	9.76 MPa	1420 psi	-20% change after 72 hours @ 250°C; ASTM D412
	12.2 MPa	1770 psi	ASTM D412
Elongation at Break	265.5 %	265.5 %	-10% change after 72 hours @ 250°C; ASTM D412
	295 %	295 %	ASTM D412
Compression Set	18 %	18 %	24 hours @ 200°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	
Minimum Service Temperature, Air	-20.0 °C	-4.00 °F	
Flash Point	>= 315 °C	>= 599 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China