

Precision Polymer Engineering V75K Fluoroelastomer Compound

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Fluoroelastomer Rubber, 70-80 °IRHD. Terpolymer of vinylidene fluoride, hexafluoropropylene and tetrafluoroethylene. To meet ASTM D2000 line call-out: MHK710, A1-10, B37, B38, EF31, E078, Z1. Where Z1 = hardness 70-80. ASTM designation = FKM. ISO designation = FPM. Applications: Excellent resistance to oils, fuels and hydraulic fluids at high temperature. Chemical resistance superior to that of standard fluoroelastomer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-V75K-Fluoroelastomer-Compound.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	75	75	°IRHD; ASTM D1415
	85	85	°IRHD, +10 change after 72 hours @ 250°C; ASTM D1415
Tensile Strength, Yield	7.50 MPa	1090 psi	-25% change after 72 hours @ 250°C; ASTM D412
	10.0 MPa	1450 psi	ASTM D412
Elongation at Break	131.25 %	131.25 %	-25% change after 72 hours @ 250°C; ASTM D412
	175 %	175 %	ASTM D412
Compression Set	17 %	17 %	24 hours @ 200°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	
Minimum Service Temperature, Air	-15.0 °C	5.00 °F	
Flash Point	>= 315 °C	>= 599 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China