

Precision Polymer Engineering V90B Fluoroelastomer Compound

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Fluoroelastomer Rubber, 85-95 °IRHD. Copolymer of vinylidene fluoride and hexafluoropropylene. To meet ASTM D2000 line call-out:- M5HK910, A1-11, B38, EF31, E078, F15, Z1. Where Z1 = compression set 30% max. ASTM designation = FKM. ISO designation = FPM. Applications: Excellent resistance to oils, fuels and hydraulic fluids at high temperature.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-V90B-Fluoroelastomer-Compound.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90	90	°IRHD; ASTM D1415
	100	100	°IRHD, +10 change after 72 hours @ 250°C; ASTM D1415
Tensile Strength, Yield	9.525 MPa	1381 psi	-25% change after 72 hours @ 250°C; ASTM D412
	12.7 MPa	1840 psi	ASTM D412
Elongation at Break	72.25 %	72.25 %	-15% change after 72 hours @ 250°C; ASTM D412
	85 %	85 %	ASTM D412
Compression Set	10 %	10 %	24 hours @ 200°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	
Minimum Service Temperature, Air	-20.0 °C	-4.00 °F	
Flash Point	>= 315 °C	>= 599 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China