

Precision Polymer Engineering V90M Fluoroelastomer Compound

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Brown Fluoroelastomer Rubber, 85-95 °IRHD. Copolymer of vinylidene fluoride and hexafluoropropylene. To meet ASTM D2000 line call-out: M3HK914, A1-10, B38, EF31, EO78, Z1, Z2, where Z1 = Brown and Z2 = Comp-set 30% max. ASTM designation = FKM. ISO designation = FPM. Applications: Excellent resistance to oils, fuels and hydraulic fluids at high temperatures.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-V90M-Fluoroelastomer-Compound.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90	90	°IRHD; ASTM D1415
	100	100	°IRHD, +10 change after 72 hours @ 250°C; ASTM D1415
Tensile Strength, Yield	10.5 MPa	1520 psi	-25% change after 72 hours @ 250°C; ASTM D412
	14.0 MPa	2030 psi	ASTM D412
Elongation at Break	75 %	75 %	-25% change after 72 hours @ 250°C; ASTM D412
	100 %	100 %	ASTM D412
Compression Set	30 %	30 %	24 hours @ 200°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	
Minimum Service Temperature, Air	-20.0 °C	-4.00 °F	
Flash Point	>= 315 °C	>= 599 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China