

Precision Polymer Engineering Z90B Hydrogenated NBR Compound

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Peroxide cured, Hydrogenated Nitrile Rubber, 85-95 °IRHD. Medium acrylonitrile content (ACN = 36%). ASTM designation = HNBR. To meet ASTM D2000 line call-out M2DH920, A26, B16, EO16, EO36, F14. Applications: High strength and excellent chemical resistance. Higher operating temperature standard nitrile. Suitable for use with sour (H2S) crude oil and gas, which may also include lubricating, oil additives and amine corrosion inhibitors. Good resistance to weathering and ozone.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-Z90B-Hydrogenated-NBR-Compound.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90	90	°IRHD; ASTM D1415
	100	100	°IRHD, +10 change after 70 hours @ 150°C; ASTM D1415
Tensile Strength, Yield	15.0 MPa	2180 psi	-25% change after 70 hours @ 150°C; ASTM D412
	20.0 MPa	2900 psi	ASTM D412
Elongation at Break	70 %	70 %	-30% change after 70 hours @ 150°C; ASTM D412
	100 %	100 %	ASTM D412
Compression Set	30 %	30 %	22 hours @ 150°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 °C	356 °F	
Minimum Service Temperature, Air	-20.0 °C	-4.00 °F	
	-18.0 °C	-0.400 °F	Non-brittle after 3 minutes
Flash Point	>= 300 °C	>= 572 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China