

## Premix Premi-Glas® 1200-10 Fiberglass Reinforced Thermoset SMC

Category : Polymer , Thermoset , Filled/Reinforced Thermoset

### Material Notes:

Premi-Glas® 1200-10 is a fiberglass reinforced thermoset sheet molding compound for general purpose applications requiring thermal stability and stiffness. Key features and benefits are: Excellent stiffness to weight ratio, non-melting Good dimensional stability, including excellent thermal resistance Pigmentable for molded-in color; best appearance with mold texture Excellent property retention in cold and hot environments Good corrosion resistance except in acid environments. Designed for compression molding in matched metal die molds. Information provided by Premix.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Premix-Premi-Glas-1200-10-Fiberglass-Reinforced-Thermoset-SMC.php](http://www.lookpolymers.com/polymer_Premix-Premi-Glas-1200-10-Fiberglass-Reinforced-Thermoset-SMC.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.70 - 1.85 g/cc	1.70 - 1.85 g/cc	
Linear Mold Shrinkage	0.0020 - 0.0035 cm/cm	0.0020 - 0.0035 in/in	Polymerization Shrinkage

Mechanical Properties	Metric	English	Comments
Tensile Strength	20.0 MPa	2900 psi	ASTM D638
Tensile Modulus	11.0 GPa	1600 ksi	ASTM D638
Flexural Strength	70.0 MPa	10200 psi	ASTM D790
Flexural Modulus	9.50 GPa	1380 ksi	ASTM D790
Compressive Strength	120 MPa	17400 psi	ASTM D695
Poissons Ratio	0.30	0.30	
Shear Modulus	4.20 GPa	609 ksi	Calculated
Izod Impact, Notched	3.10 J/cm	5.81 ft-lb/in	ASTM D256
Izod Impact, Unnotched	3.65 J/cm	6.84 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	35.0 $\mu\text{m}/\text{m}^{\circ}\text{C}$	19.4 $\mu\text{in}/\text{in}^{\circ}\text{F}$	Z Direction
CTE, linear, Transverse to Flow	25.0 $\mu\text{m}/\text{m}^{\circ}\text{C}$	13.9 $\mu\text{in}/\text{in}^{\circ}\text{F}$	XY Direction
Thermal Conductivity	0.300 W/m-K	2.08 BTU-in/hr-ft <sup>2</sup> -°F	

Processing Properties	Metric	English	Comments
Processing Temperature	150 °C	302 °F	Compression Molding

Processing Properties	Metric	English	Comments
Clamp Pressure	50.00 6.89 MPa	50.00 1000 psi	Molding Pressure

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China