

## Premix Thermoplastics PRE-ELEC® PP 1373

Category : Polymer , Thermoplastic , Polypropylene (PP)

### Material Notes:

PRE-ELEC PP 1373 is a conductive thermoplastic compound based on polypropylene. Conductivity is achieved by using special conductive carbon black. In addition to a low electrical resistivity PRE-ELEC PP 1373 has an excellent balance of mechanical properties and is easy to injection mould. Typical applications include injection molded crates, boxes and tote bins for electronic components and other static sensitive devices (SSD). Test Specimen - 4.0 mm thick, 10.0 mm wide molded rod. Information provided by Premix Thermoplastics Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Premix-Thermoplastics-PRE-ELEC-PP-1373.php](http://www.lookpolymers.com/polymer_Premix-Thermoplastics-PRE-ELEC-PP-1373.php)

Physical Properties	Metric	English	Comments
Density	1.09 g/cc	0.0394 lb/in <sup>3</sup>	
Linear Mold Shrinkage	0.0080 - 0.012 cm/cm	0.0080 - 0.012 in/in	ISO 294-4
Melt Flow	0.30 g/10 min	0.30 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	
	4.0 g/10 min	4.0 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 230 °C	@Load 11.0 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	100	100	ISO 868
Hardness, Shore D	73	73	ISO 868
Tensile Strength, Ultimate	20.0 MPa	2900 psi	ISO 527
Tensile Strength, Yield	26.0 MPa	3770 psi	ISO 527
Elongation at Break	67 %	67 %	ISO 527
Elongation at Yield	5.0 %	5.0 %	ISO 527
Modulus of Elasticity	2.10 GPa	305 ksi	ISO 178
Izod Impact, Notched	1.40 J/cm	2.62 ft-lb/in	ISO 180
	@Thickness 4.00 mm, Temperature 23.0 °C	@Thickness 0.157 in, Temperature 73.4 °F	
Izod Impact, Unnotched	7.70 J/cm	14.4 ft-lb/in	ISO 180
	@Thickness 4.00 mm, Temperature 23.0 °C	@Thickness 0.157 in, Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	116 °C	241 °F	ISO 75/Method Bf
Vicat Softening Point	153 °C	307 °F	Rate A; ISO 306/A50

Electrical Properties	Metric	English	Comments
Volume Resistivity	<= 1000 ohm-cm	<= 1000 ohm-cm	ISO D-257
Surface Resistance	<= 10000 ohm	<= 10000 ohm	ISO D-257

Processing Properties	Metric	English	Comments
Melt Temperature	200 - 250 °C	392 - 482 °F	
Mold Temperature	60.0 - 80.0 °C	140 - 176 °F	
Drying Temperature	60.0 - 80.0 °C @Time 7200 - 14400 sec	140 - 176 °F @Time 2.00 - 4.00 hour	Pre-drying
Moisture Content	<= 0.15 %	<= 0.15 %	When Produced
Injection Pressure	60.0 - 80.0 MPa	8700 - 11600 psi	
Shelf Life	12.0 Month	12.0 Month	Normal Storing Conditions

Descriptive Properties	Value	Comments
Appearance	Granule	
Color	Black	
Injection Speed	Moderate	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China