

## Pyrotek O-1 Low-Temperature Felt

Category : Ceramic

### Material Notes:

Excellent resistance to vibration. Not effected by 1.55 MPa steam. Dimensions 1524 mm x 22.9 m 6, 13, 25 mm thick Applications High-density gaskets at elevated temperatures Initial systems, high pressure systems and air collection systems Information provided by Pyrotek.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Pyrotek-O-1-Low-Temperature-Felt.php](http://www.lookpolymers.com/polymer_Pyrotek-O-1-Low-Temperature-Felt.php)

Physical Properties	Metric	English	Comments
Density	0.256 g/cc	0.00925 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	0.0700 MPa	10.2 psi	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	650 °C	1200 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China