

Pyrotek Pyroboard™ S1090 Roller

Category : Ceramic

Material Notes:

Pyroboard™ S1090 is used in cooling and preheat areas of the furnace where the temperature does not exceed 1600° F. Information provided by Pyrotek.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Pyrotek-Pyroboard-S1090-Roller.php

Physical Properties	Metric	English	Comments
Density	0.881 g/cc	0.0318 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	2.34 MPa	339 psi	
Compressive Strength	2.07 MPa	300 psi	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.156 W/m-K	1.08 BTU-in/hr-ft ² -°F	
Maximum Service Temperature, Air	1093 °C	1999 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China