

Pyrotek Pyrocast ZC Refractory Shapes

Category : Ceramic , Oxide , Aluminum Oxide , Silicon Oxide

Material Notes:

Aggregate Base: MulliteApplicationsDoor sill Breech plug Door jamb Information provided by Pyrotek.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Pyrotek-Pyrocast-ZC-Refractory-Shapes.php

Physical Properties	Metric	English	Comments
Density	2.74 g/cc	0.0990 lb/in ³	

Mechanical Properties	Metric	English	Comments
Compressive Strength	68.95 - 96.53 MPa	10000 - 14000 psi	after 816°C
Abrasion	4.0 - 8.0	4.0 - 8.0	Resistance (CC Loss) ASTM C704

Thermal Properties	Metric	English	Comments
CTE, linear	6.12 $\mu\text{m}/\text{m}\cdot\text{°C}$	3.40 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Thermal Conductivity	1.67 W/m-K	11.6 BTU-in/hr-ft ² -°F	
	@Temperature 538 °C	@Temperature 1000 °F	
Maximum Service Temperature, Air	1649 °C	3000 °F	

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	63.5 %	63.5 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China