

## Quadrant EPP Fluorosint® 500 PTFE, synthetic mica-filled PTFE, compression molded (ASTM Product Data Sheet)

Category : Polymer , Thermoplastic , Fluoropolymer , PTFE , Polytetrafluoroethylene (PTFE), Mica Filled

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Quadrant-EPP-Fluorosint-500-PTFE-synthetic-mica-filled-PTFE-compression-molded-ASTM-Product-Data-Sheet.php](http://www.lookpolymers.com/polymer_Quadrant-EPP-Fluorosint-500-PTFE-synthetic-mica-filled-PTFE-compression-molded-ASTM-Product-Data-Sheet.php)

Physical Properties	Metric	English	Comments
Specific Gravity	2.32 g/cc	2.32 g/cc	ASTM D792
Water Absorption	0.10 %	0.10 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	0.30 %	0.30 %	Immersion; ASTM D570(2)
Deformation	5.0 %	5.0 %	2000 psi; 122°F (50°C)

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	55	55	ASTM D785
Hardness, Shore D	70	70	ASTM D2240
Tensile Strength	7.58 MPa	1100 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Tensile Modulus	2.07 GPa	300 ksi	ASTM D638
Flexural Strength	15.2 MPa	2200 psi	ASTM D790
Flexural Modulus	3.45 GPa	500 ksi	ASTM D790
Compressive Strength	27.6 MPa	4000 psi	10% Def.; ASTM D695
Compressive Modulus	1.72 GPa	250 ksi	ASTM D695
Shear Strength	14.5 MPa	2100 psi	ASTM D732
Izod Impact, Notched	0.481 J/cm	0.900 ft-lb/in	ASTM D256 Type A
Coefficient of Friction, Dynamic	0.15	0.15	Dry vs. Steel; QTM55007
K (wear) Factor	1210 x 10 <sup>-8</sup> mm <sup>3</sup> /N-M	600 x 10 <sup>-10</sup> in <sup>3</sup> -min/ft-lb-hr	QTM 55010
Limiting Pressure Velocity	0.280 MPa-m/sec	8000 psi-ft/min	4:1 safety factor; QTM 55007

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
CTE, linear	@Temperature -40.0 - 149 °C	@Temperature -40.0 - 300 °F	ASTM E831
Thermal Conductivity	0.764 W/m-K	5.30 BTU-in/hr-ft <sup>2</sup> -°F	ASTM F433
Melting Point	327 °C	621 °F	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	260 °C	500 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	132 °C	270 °F	ASTM D648
Flammability, UL94	V-0	V-0	1/8 inch (Estimated Rating)

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	>= 1.00e+13 ohm	>= 1.00e+13 ohm	EOS/ESD S11.11
Dielectric Constant	2.85	2.85	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	10.8 kV/mm	275 kV/in	Short Term; ASTM D149
Dissipation Factor	0.0080	0.0080	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	No	No	
NSF	No	No	
USDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Acceptable	Acceptable	
Acids, Weak	Acceptable	Acceptable	
Alcohols	Acceptable	Acceptable	
Alkalies, Strong (pH 11-14)	Unacceptable	Unacceptable	
Alkalies, Weak	Acceptable	Acceptable	

Chemical Resistance Properties	Metric	English	Comments
Chlorinated Solvents	Acceptable	Acceptable	
Conductive / Static Dissipative	No	No	
Continuous Sunlight	Acceptable	Acceptable	
Hot Water / Steam	Limited	Limited	
Hydrocarbons - Aliphatic	Acceptable	Acceptable	
Hydrocarbons - Aromatic	Acceptable	Acceptable	
Inorganic Salt Solutions	Acceptable	Acceptable	
Ketones, Esters	Acceptable	Acceptable	

Descriptive Properties	Value	Comments
Color	Natural	
Machinability	2	1-10, 1=Easier to Machine

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China