

## Quadrant EPP Ketron® 1000 IM Injection Molded Unfilled Polyetheretherketone (ASTM Product Data Sheet)

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Unreinforced

### Material Notes:

Excellent chemical resistance Very low moisture absorption Inherently good wear and abrasion resistance Unaffected by continuous exposure to hot water or steam

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Quadrant-EPP-Ketron-1000-IM-Injection-Molded-Unfilled-Polyetheretherketone-ASTM-Product-Data-Sheet.php](http://www.lookpolymers.com/polymer_Quadrant-EPP-Ketron-1000-IM-Injection-Molded-Unfilled-Polyetheretherketone-ASTM-Product-Data-Sheet.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.31 g/cc	1.31 g/cc	ASTM D792
Water Absorption	0.10 %	0.10 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	0.50 %	0.50 %	ASTM D 570(2)

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	107	107	ASTM D785
Hardness, Rockwell R	127	127	ASTM D785
Hardness, Shore D	88	88	ASTM D2240
Tensile Strength	110 MPa	16000 psi	ASTM D638
Elongation at Break	25 %	25 %	ASTM D638
Tensile Modulus	4.14 GPa	600 ksi	ASTM D638
Flexural Strength	159 MPa	23000 psi	ASTM D790
Flexural Modulus	4.14 GPa	600 ksi	ASTM D790
Compressive Strength	138 MPa	20000 psi	10% Def.; ASTM D695
Compressive Modulus	2.93 GPa	425 ksi	ASTM D695
Izod Impact, Notched	0.21 J/cm	0.40 ft-lb/in	ASTM D256 Type A
Coefficient of Friction, Dynamic	0.32	0.32	Dry vs. Steel; QTM55007
K (wear) Factor	755 x 10 <sup>-8</sup> mm <sup>3</sup> /N-M	375 x 10 <sup>-10</sup> in <sup>3</sup> -min/ft-lb-hr	QTM 55010
Limiting Pressure Velocity	0.298 MPa-m/sec	8500 psi-ft/min	4:1 safety factor; QTM 55007

Thermal Properties	Metric	English	Comments
CTE, linear	46.8 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	26.0 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ASTM E831
	@Temperature -40.0 - 150 $^{\circ}\text{C}$	@Temperature -40.0 - 302 $^{\circ}\text{F}$	
Thermal Conductivity	0.252 W/m-K	1.75 BTU-in/hr-ft <sup>2</sup> - $^{\circ}\text{F}$	ASTM E1530-11
Melting Point	340 $^{\circ}\text{C}$	644 $^{\circ}\text{F}$	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	249 $^{\circ}\text{C}$	480 $^{\circ}\text{F}$	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	160 $^{\circ}\text{C}$	320 $^{\circ}\text{F}$	ASTM D648
Flammability, UL94	V-0	V-0	1/8 inch (Estimated Rating)

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	$\geq 1\text{e}+13$ ohm	$\geq 1\text{e}+13$ ohm	ASTM D257
Dielectric Constant	3.3	3.3	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	18.9 kV/mm	480 kV/in	Short Term; ASTM D149
Dissipation Factor	0.003	0.003	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China