

## Quadrant EPP Nylatron® GSM Blue Nylon, Cast Oil & MoS2 Filled Type 6 (ASTM Product Data Sheet)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, MoS2 Filled

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Quadrant-EPP-Nylatron-GSM-Blue-Nylon-Cast-Oil-MoS2-Filled-Type-6-ASTM-Product-Data-Sheet.php](http://www.lookpolymers.com/polymer_Quadrant-EPP-Nylatron-GSM-Blue-Nylon-Cast-Oil-MoS2-Filled-Type-6-ASTM-Product-Data-Sheet.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D792
Water Absorption	0.30 %	0.30 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	6.0 %	6.0 %	Immersion; ASTM D570(2)

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	80	80	ASTM D785
Hardness, Rockwell R	117	117	ASTM D785
Tensile Strength	68.9 MPa	10000 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Tensile Modulus	3.45 GPa	500 ksi	ASTM D638
Flexural Strength	103 MPa	15000 psi	ASTM D790
Flexural Modulus	3.45 GPa	500 ksi	ASTM D790
Compressive Strength	89.6 MPa	13000 psi	10% Def.; ASTM D695
Compressive Modulus	2.93 GPa	425 ksi	ASTM D695
Izod Impact, Notched	0.481 J/cm	0.900 ft-lb/in	ASTM D256 Type A
Coefficient of Friction, Dynamic	0.18	0.18	Dry vs. Steel; QTM55007
K (wear) Factor	131 x 10 <sup>-8</sup> mm <sup>3</sup> /N-M	65.0 x 10 <sup>-10</sup> in <sup>3</sup> -min/ft-lb-hr	QTM 55010
Limiting Pressure Velocity	0.193 MPa-m/sec	5500 psi-ft/min	4:1 safety factor; QTM 55007

Thermal Properties	Metric	English	Comments
CTE, linear	99.0 μm/m-°C	55.0 μin/in-°F	ASTM E831
	@Temperature -40.0 - 149 °C	@Temperature -40.0 - 300 °F	

Thermal Properties	Metric	English	Comments <small>Peak; ASTM D3418</small>
Maximum Service Temperature, Air	93.3 °C	200 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	93.3 °C	200 °F	ASTM D648
Flammability, UL94	HB	HB	1/8 inch (Estimated Rating)

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	>= 1.00e+13 ohm	>= 1.00e+13 ohm	EOS/ESD S11.11

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	No	No	
NSF	No	No	
USDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Unacceptable	Unacceptable	
Acids, Weak	Limited	Limited	
Alcohols	Limited	Limited	
Alkalies, Strong (pH 11-14)	Unacceptable	Unacceptable	
Alkalies, Weak	Limited	Limited	
Chlorinated Solvents	Limited	Limited	
Conductive / Static Dissipative	No	No	
Continuous Sunlight	Limited	Limited	
Hot Water / Steam	Limited	Limited	
Hydrocarbons - Aliphatic	Acceptable	Acceptable	
Hydrocarbons - Aromatic	Acceptable	Acceptable	
Inorganic Salt Solutions	Acceptable	Acceptable	

<small>Ketones, Esters</small> Chemical Resistance Properties	<small>Acceptable</small> Metric	<small>Acceptable</small> English	Comments
<b>Descriptive Properties</b>	<b>Value</b>		<b>Comments</b>
Color	Dark Blue		
Machinability	1		1-10, 1=Easier to Machine

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China