

Quadrant EPP TIVAR® 1000 EC PE-UHMW + specific additives (ISO Data)

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), UHMW PE Ultra High Molecular Weight

Material Notes:

TIVAR 1000 EC is a PE-UHMW grade containing specific additives rendering this material a lower surface resistivity than TIVAR 1000 antistatic, improving electrical conductivity and UV-resistance

Order this product through the following link:

http://www.lookpolymers.com/polymer_Quadrant-EPP-TIVAR-1000-EC-PE-UHMW-specific-additives-ISO-Data.php

Physical Properties	Metric	English	Comments
Density	0.945 g/cc	0.0341 lb/in ³	ISO 1183-1
Water Absorption	<= 0.10 %	<= 0.10 %	96 hr; ISO 62
Moisture Absorption at Equilibrium	<= 0.10 %	<= 0.10 %	50% RH
Water Absorption at Saturation	<= 0.10 %	<= 0.10 %	ISO 62
Outgassing - Total Mass Loss	0.14 %	0.14 %	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	62	62	
Ball Indentation Hardness	35.0 MPa	5080 psi	ISO 2039-1
Tensile Strength	21.0 MPa	3050 psi	at Yield; ISO 527-1/-2
Elongation at Break	>= 50 %	>= 50 %	ISO 527-1/-2
Elongation at Yield	15 %	15 %	ISO 527-1/-2
Tensile Modulus	0.825 GPa	120 ksi	ISO 527-1/-2
Flexural Strength	20.0 MPa	2900 psi	
Compressive Strength	7.50 MPa	1090 psi	ISO 604
	@Strain 1 %	@Strain 1 %	
	12.0 MPa	1740 psi	
	@Strain 2 %	@Strain 2 %	ISO 604
	19.0 MPa	2760 psi	ISO 604
	@Strain 5 %	@Strain 5 %	
K Factor (ISO)	8.0 µm/km	8.0 µm/km	
Charpy Impact Unnotched	NB	NB	ISO 179-1/1eU

Charpy Impact, Notched Mechanical Properties	10.5 J/cm ² Metric	50.0 ft-lb/in ² English	Partial Break; ISO 179-1/1eA Comments
Coefficient of Friction, Dynamic	0.15 - 0.30	0.15 - 0.30	
Sand Slurry	100	100	
Limiting Pressure Velocity	0.0500 MPa-m/sec	1430 psi-ft/min	at 1 m/s unlubricated
	0.0800 MPa-m/sec	2280 psi-ft/min	at 0.1 m/s unlubricated

Thermal Properties	Metric	English	Comments
CTE, linear	200 µm/m-°C	111 µin/in-°F	
	@Temperature 23.0 - 100 °C	@Temperature 73.4 - 212 °F	
Thermal Conductivity	0.400 W/m-K	2.78 BTU-in/hr-ft ² -°F	
Melting Point	135 °C	275 °F	DSC, 10°C/min.; ISO 11357-1/-3
Maximum Service Temperature, Air	80.0 °C	176 °F	Continuous
Deflection Temperature at 1.8 MPa (264 psi)	42.0 °C	108 °F	ISO 75-1/-2
Flammability, UL94	HB	HB	
Oxygen Index	<= 20 %	<= 20 %	ISO 4589-1/-2

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	<= 1e+05	<= 1e+05	IEC 60093

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
European Food 1935/2004	Yes	Yes	
FDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Acceptable	Acceptable	
Acids, Weak	Acceptable	Acceptable	
Alcohols	Acceptable	Acceptable	
Alkalies, Strong (pH 11-14)	Acceptable	Acceptable	

Chemical Resistance Properties	Metric	English	Comments
Chlorinated Solvents	Acceptable	Acceptable	
Conductive / Static Dissipative	Yes	Yes	
Continuous Sunlight	Limited	Limited	
Hot Water / Steam	Unacceptable	Unacceptable	
Hydrocarbons - Aliphatic	Acceptable	Acceptable	
Hydrocarbons - Aromatic	Limited	Limited	
Inorganic Salt Solutions	Acceptable	Acceptable	
Ketones, Esters	Acceptable	Acceptable	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China