

Quadrant EPP TIVAR® 1000 UV Stabilized UHMW-PE, Natural & Colored Except Black (ASTM Product Data Sheet)

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), UHMW PE Ultra High Molecular Weight

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Quadrant-EPP-TIVAR-1000-UV-Stabilized-UHMW-PE-Natural-Colored-Except-Black-ASTM-Product-Data-Sheet.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.930 g/cc	0.930 g/cc	ASTM D792
Water Absorption	<= 0.010 %	<= 0.010 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	<= 0.010 %	<= 0.010 %	Immersion; ASTM D570(2)

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	66	66	ASTM D2240
Tensile Strength	40.0 MPa	5800 psi	ASTM D638
Elongation at Break	300 %	300 %	ASTM D638
Tensile Modulus	0.800 GPa	116 ksi	ASTM D638
Flexural Strength	26.2 MPa	3800 psi	ASTM D790
Flexural Modulus	0.800 GPa	116 ksi	ASTM D790
Compressive Strength	20.7 MPa	3000 psi	10% Def.; ASTM D695
Compressive Modulus	0.552 GPa	80.0 ksi	ASTM D695
Shear Strength	33.1 MPa	4800 psi	ASTM D732
Izod Impact, Notched	NB	NB	ASTM D256 Type A
Coefficient of Friction, Dynamic	0.12	0.12	Dry vs. Steel; QTM55007
Sand Slurry	10	10	1018 Steel = 100
Limiting Pressure Velocity	0.105 MPa-m/sec	3000 psi-ft/min	4:1 safety factor; QTM 55007

Thermal Properties	Metric	English	Comments
CTE, linear	198 µm/m-°C	110 µin/in-°F	ASTM E831
	@Temperature -40.0 - 149 °C	@Temperature -40.0 - 300 °F	

Thermal Properties	0.409 W/m-K Metric	2.84 BTU-in/hr-ft ² -°F English	Comments
Melting Point	135 °C	275 °F	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	82.2 °C	180 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	46.7 °C	116 °F	ASTM D648
Flammability, UL94	HB	HB	1/8 inch (Estimated Rating)

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ASTM D257
Dielectric Constant	2.3 @Frequency 1e+6 Hz	2.3 @Frequency 1e+6 Hz	ASTM D150
Dielectric Strength	90.6 kV/mm	2300 kV/in	Short Term; ASTM D149
Dissipation Factor	0.00050 @Frequency 1e+6 Hz	0.00050 @Frequency 1e+6 Hz	ASTM D150

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	No	No	
NSF	No	No	
USDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Limited	Limited	
Acids, Weak	Acceptable	Acceptable	
Alcohols	Acceptable	Acceptable	
Alkalies, Strong (pH 11-14)	Acceptable	Acceptable	
Alkalies, Weak	Acceptable	Acceptable	
Chlorinated Solvents	Acceptable	Acceptable	
Conductive / Static Dissipative	No	No	

Chemical Resistance Properties	Metric able	English ble	Comments
Hot Water / Steam	Limited	Limited	
Hydrocarbons - Aliphatic	Acceptable	Acceptable	
Hydrocarbons - Aromatic	Unacceptable	Unacceptable	
Inorganic Salt Solutions	Acceptable	Acceptable	
Ketones, Esters	Limited	Limited	

Descriptive Properties	Value	Comments
Machinability	3	1-10, 1=Easier to Machine

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China