

Quadrant EPP TIVAR® HPV UHMW-PE (ASTM Product Data Sheet)

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), UHMW PE Ultra High Molecular Weight

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Quadrant-EPP-TIVAR-HPV-UHMW-PE-ASTM-Product-Data-Sheet.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.930 g/cc	0.930 g/cc	ASTM D792
Water Absorption	<= 0.010 %	<= 0.010 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	<= 0.010 %	<= 0.010 %	Immersion; ASTM D570(2)

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	65	65	ASTM D2240
Tensile Strength	40.7 MPa	5900 psi	ASTM D638
Elongation at Break	39 %	39 %	ASTM D638
Tensile Modulus	0.386 GPa	56.0 ksi	ASTM D638
Flexural Strength	20.7 MPa	3000 psi	ASTM D790
Flexural Modulus	0.531 GPa	77.0 ksi	ASTM D790
Compressive Strength	20.7 MPa	3000 psi	10% Def.; ASTM D695
Compressive Modulus	0.531 GPa	77.0 ksi	ASTM D695
Izod Impact, Notched	29.4 J/cm	55.0 ft-lb/in	ASTM D4020
Coefficient of Friction, Dynamic	0.090	0.090	Dry vs. Steel; QTM55007
Sand Slurry	16.5	16.5	1018 Steel = 100
Limiting Pressure Velocity	0.210 MPa-m/sec	6000 psi-ft/min	4:1 safety factor; QTM 55007

Thermal Properties	Metric	English	Comments
CTE, linear	144 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	80.0 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ASTM E831
	@Temperature -40.0 - 149 $^{\circ}\text{C}$	@Temperature -40.0 - 300 $^{\circ}\text{F}$	
Melting Point	135 $^{\circ}\text{C}$	275 $^{\circ}\text{F}$	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	82.2 $^{\circ}\text{C}$	180 $^{\circ}\text{F}$	Long Term

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (100 psi)	46.7 °C	116 °F	ASTM D648
Flammability, UL94	HB	HB	1/8 inch (Estimated Rating)

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	>= 1e+14 ohm	>= 1e+14 ohm	ASTM D257

Descriptive Properties	Value	Comments
Sand Water Wheel	101	ASTM G65; TIVAR® 1000 = 100

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China