

Quadrant EPP Techtron® HPV PPS (ASTM Product Data Sheet)

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS), Unreinforced, Extruded

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Quadrant-EPP-Techtron-HPV-PPS-ASTM-Product-Data-Sheet.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.43 g/cc	1.43 g/cc	ASTM D792
Water Absorption	0.010 %	0.010 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	0.090 %	0.090 %	Immersion; ASTM D570(2)

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	84	84	ASTM D785
Tensile Strength	75.2 MPa	10900 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Tensile Modulus	3.72 GPa	540 ksi	ASTM D638
Flexural Strength	72.4 MPa	10500 psi	ASTM D790
Flexural Modulus	3.69 GPa	535 ksi	ASTM D790
Compressive Strength	107 MPa	15500 psi	10% Def.; ASTM D695
Compressive Modulus	2.36 GPa	342 ksi	ASTM D695
Izod Impact, Notched	0.747 J/cm	1.40 ft-lb/in	ASTM D256 Type A
Coefficient of Friction, Dynamic	0.20	0.20	Dry vs. Steel; QTM55007
K (wear) Factor	125 x 10 ⁻⁸ mm ³ /N-M	62.0 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	QTM 55010
Limiting Pressure Velocity	0.307 MPa-m/sec	8750 psi-ft/min	4:1 safety factor; QTM 55007

Thermal Properties	Metric	English	Comments
CTE, linear	59.4 μm/m-°C	33.0 μin/in-°F	ASTM E831
	@Temperature -40.0 - 149 °C	@Temperature -40.0 - 300 °F	
Thermal Conductivity	0.303 W/m-K	2.10 BTU-in/hr-ft ² -°F	ASTM F433
Melting Point	280 °C	536 °F	Crystalline, Peak; ASTM D3418

Thermal Properties <small>Temperature, Air</small>	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	116 °C	240 °F	ASTM D648
Flammability, UL94	V-0	V-0	1/8 inch (Estimated Rating)

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	>= 1.00e+13 ohm	>= 1.00e+13 ohm	EOS/ESD S11.11
Dielectric Strength	19.7 kV/mm	500 kV/in	Short Term; ASTM D149

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	Yes	Yes	
NSF	No	No	
USDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Limited	Limited	
Acids, Weak	Acceptable	Acceptable	
Alcohols	Acceptable	Acceptable	
Alkalies, Strong (pH 11-14)	Acceptable	Acceptable	
Alkalies, Weak	Acceptable	Acceptable	
Chlorinated Solvents	Acceptable	Acceptable	
Conductive / Static Dissipative	No	No	
Continuous Sunlight	Limited	Limited	
Hot Water / Steam	Acceptable	Acceptable	
Hydrocarbons - Aliphatic	Acceptable	Acceptable	
Hydrocarbons - Aromatic	Acceptable	Acceptable	
Inorganic Salt Solutions	Acceptable	Acceptable	

<small>Ketones, Esters</small> Chemical Resistance Properties	<small>Acceptable</small> Metric	<small>Acceptable</small> English	Comments
Descriptive Properties	Value	Comments	
Machinability	3	1-10, 1=Easier to Machine	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China