

Qualchem Danamid AFGFS2HUV14 Polyamide 66, 14% Glass Fiber

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Reinforced with glass fiber. Impact modified, heat and UV stabilized, for long-lasting use at 120-140°C, resistant to artificial lights. Information provided by Qualchem Zrt.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Qualchem-Danamid-AFGFS2HUV14-Polyamide-66-14-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.32 g/cc	0.0477 lb/in ³	DIN 53479
Filler Content	12 - 16 %	12 - 16 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	>= 70.0 MPa	>= 10200 psi	50 mm/min; ISO 527-1,2
Charpy Impact Unnotched	>= 1.50 J/cm ² @Temperature 23.0 °C	>= 7.14 ft-lb/in ² @Temperature 73.4 °F	DIN 53453
Charpy Impact, Notched	>= 0.500 J/cm ² @Temperature 23.0 °C	>= 2.38 ft-lb/in ² @Temperature 73.4 °F	DIN 53453

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	DIN 53461
Deflection Temperature at 1.8 MPa (264 psi)	220 °C	428 °F	DIN 53461
Flammability, UL94	HB @Thickness 4.00 mm	HB @Thickness 0.157 in	MSZ 10383

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	DIN 53482
Comparative Tracking Index	550 V	550 V	IEC 112

Processing Properties	Metric	English	Comments
Moisture Content	2.0 - 2.2 %	2.0 - 2.2 %	DIN 53714

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China