

Qualchem Danamid FGF-15 Polyamide 6, 15% Glass Fiber

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Reinforced with glass fiber. Information provided by Qualchem Zrt.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Qualchem-Danamid-FGF-15-Polyamide-6-15-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	DIN 53479
Filler Content	13 - 17 %	13 - 17 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 120 MPa	<= 17400 psi	50 mm/min; ISO 527-1,2
Elongation at Break	4.0 %	4.0 %	ISO 527-1,2
Tensile Modulus	5.70 GPa	827 ksi	ISO 527-1,2
Flexural Strength	200 MPa	29000 psi	10mm/min; DIN 53452
Charpy Impact Unnotched	<= 3.00 J/cm ² @Temperature 23.0 °C	<= 14.3 ft-lb/in ² @Temperature 73.4 °F	DIN 53453
Charpy Impact, Notched	<= 0.500 J/cm ² @Temperature 23.0 °C	<= 2.38 ft-lb/in ² @Temperature 73.4 °F	DIN 53453

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	200 °C	392 °F	DIN 53461
Deflection Temperature at 1.8 MPa (264 psi)	190 °C	374 °F	DIN 53461
Flammability, UL94	HB @Thickness 4.00 mm	HB @Thickness 0.157 in	MSZ 10383

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	DIN 53482
Comparative Tracking Index	550 V	550 V	IEC 112

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Moisture Content	2.0 - 2.2 %	2.0 - 2.2 %	DIN 53714
Processing Properties	Metric	English	Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China