

R70-068 Styrene-based Biomedical Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Styrenic TPE

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_R70-068-Styrene-based-Biomedical-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.930 g/cc	0.930 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50	50	ASTM D2240
Tensile Strength, Ultimate	11.2 MPa	1630 psi	ASTM D412
Tensile Strength, Yield	0.965 MPa	140 psi	at 100%; ASTM D412
Elongation at Break	850 %	850 %	ASTM D412
Tear Strength	19.3 kN/m	110 pli	die B; ASTM D624
Compression Set	38 %	38 %	ASTM D395

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China