

RExtac Rextac® RT 1215 Amorphous Polyalphaolefin (APAO)

Category : Polymer , Thermoplastic , Polyalphaolefin , Polyolefin

Material Notes:

Laminate Grade.Description: Ethylene copolymer and FDA compliantFeatures: Good heat resistance, short open time, and excellent wetting propertiesApplications: Lamination of reinforced tapes and protective overwrapsOther Properties: Ring and Ball Softening Point (ASTM E 28): 143°C.Needle Penetration (ASTM D 1321): 20 mm.Shear Adhesion Failure Temperature (SAFT), Kraft/Kraft (Huntsman Method): 112°C.Open Time, Kraft/Kraft (Huntsman Method): 10 sec.Melt Density (190°C; Huntsman Method): 0.74 g/cc.Flashpoint, COC (ASTM D 93): >235°C.Information provided by Huntsman Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_REXTac-Rextac-RT-1215-Amorphous-Polyalphaolefin-APAO.php

Physical Properties	Metric	English	Comments
Density	0.860 g/cc	0.0311 lb/in ³	ASTM D 792
Viscosity	1500 cP @Temperature 190 °C	1500 cP @Temperature 374 °F	melt viscosity; ASTM D 3236

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-22.0 °C	-7.60 °F	ASTM D3417

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China