

## RExtac Rextac® RT 1230 Amorphous Polyalphaolefin (APAO)

Category : Polymer , Thermoplastic , Polyalphaolefin , Polyolefin

### Material Notes:

Laminate Grade.Description: Ethylene copolymer and FDA compliantFeatures: Good heat resistance, short open time, and excellent wetting propertiesApplications: Lamination of reinforced tapes and protective overwrapsOther Properties: Ring and Ball Softening Point (ASTM E 28): 143°C.Needle Penetration (ASTM D 1321): 13 mm.Shear Adhesion Failure Temperature (SAFT), Kraft/Kraft (Huntsman Method): 112°C.Open Time, Kraft/Kraft (Huntsman Method): 10 sec.Melt Density (190°C; Huntsman Method): 0.74 g/cc.Flashpoint, COC (ASTM D 93): >235°C.Information provided by Huntsman Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_REXTac-Rextac-RT-1230-Amorphous-Polyalphaolefin-APAO.php](http://www.lookpolymers.com/polymer_REXTac-Rextac-RT-1230-Amorphous-Polyalphaolefin-APAO.php)

Physical Properties	Metric	English	Comments
Density	0.860 g/cc	0.0311 lb/in <sup>3</sup>	ASTM D 792
Viscosity	3000 cP @Temperature 190 °C	3000 cP @Temperature 374 °F	melt viscosity; ASTM D 3236

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	1.03 MPa	149 psi	ASTM D 638

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-22.0 °C	-7.60 °F	ASTM D3417

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China