

## RExtac Rextac® RT 2880 Amorphous Polyalphaolefin (APAO)

Category : Polymer , Thermoplastic , Polyalphaolefin , Polyolefin

### Material Notes:

Adhesive and Sealant Grade. Description: Butene-1 copolymer and FDA compliant Features: Very low softening point and excellent tensile properties Applications: Component of hot melt adhesives, sealants and specialty products Other Properties: Ring and Ball Softening Point (ASTM E 28): 93°C. Needle Penetration (ASTM D 1321): 25 mm. Shear Adhesion Failure Temperature (SAFT), Kraft/Kraft (Huntsman Method): 93°C. Open Time, Kraft/Kraft (Huntsman Method): > 240 sec. Flashpoint, COC (ASTM D 93): >235°C. Information provided by Huntsman Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_REXtac-Rextac-RT-2880-Amorphous-Polyalphaolefin-APAO.php](http://www.lookpolymers.com/polymer_REXtac-Rextac-RT-2880-Amorphous-Polyalphaolefin-APAO.php)

Physical Properties	Metric	English	Comments
Viscosity	8000 cP @Temperature 190 °C	8000 cP @Temperature 374 °F	melt viscosity; ASTM D 3236

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	3.00 MPa	435 psi	ASTM D 638

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-35.0 °C	-31.0 °F	ASTM D3417

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China