

## Radici Radiflam® A RV250FR (cond.) Nylon 66-25GF

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , 30% Glass Fiber Filled

### Material Notes:

Radiflam® A is a range of flame retardant polyamides 66 (PA 66) used for injection molding and extrusion for all applications where high fire resistance is required. Information provided by Radici group.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Radici-Radiflam-A-RV250FR-cond-Nylon-66-25GF.php](http://www.lookpolymers.com/polymer_Radici-Radiflam-A-RV250FR-cond-Nylon-66-25GF.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	(Dry)
Water Absorption	2.4 %	2.4 %	initially dry
Moisture Absorption at Equilibrium	0.90 %	0.90 %	initially dry

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	(Dry)

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Comparative Tracking Index	600 V	600 V	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China